

PAT-NO: JP02000219950A  
DOCUMENT-IDENTIFIER: JP 2000219950 A  
TITLE: HOT-DIP Zn-Al-Mg COATED STEEL SHEET EXCELLENT IN  
CORROSION RESISTANCE AFTER COATING  
PUBN-DATE: August 8, 2000

INVENTOR-INFORMATION:

NAME	COUNTRY
FUJII, SHIRO	N/A
MORIMOTO, YASUhide	N/A
HONDA, KAZUHIKO	N/A
NIIGASHIRA, HIDETOSHI	N/A
NISHIMOTO, KAZUMI	N/A
TANAKA, AKIRA	N/A
SUEMUNE, YOSHIHIRO	N/A

ASSIGNEE-INFORMATION:

NAME	COUNTRY
NIPPON STEEL CORP	N/A

APPL-NO: JP11168167  
APPL-DATE: June 15, 1999

INT-CL (IPC): C23C002/06, C22C018/04 , C23C002/40

ABSTRACT:

PROBLEM TO BE SOLVED: To provide a hot-dip Zn-Al-Mg coated steel sheet excellent in corrosion resistance after coating mainly for being used as building material.

SOLUTION: A hot-dip metal coated layer composed by wt.% of 3.0-6.0% Al, 1.0-7.0% Mg and the balance Zn with inevitable impurities and constituted with Zn primary crystal phase and Zn-Al-Mg three component eutectic phase is provided on one side surface or both surfaces. Desirably, as substrate layer of the hot-dip metal coated layer, Ni coated layer is employed with 0.2-2 g/m<sup>2</sup>.

COPYRIGHT: (C)2000, JPO